

E.MIX EASI RENDER 09

PREMIXED CEMENT RENDER FOR BRICK, BLOCK AND FAIRFACE CONCRETE WALL, PATCHING AND GENERAL USE IN DRY OR WET INTERIOR AND EXTERIOR



EXCELLENT



E.MIX Easi Render 09 is a high quality cement-based render for application on brick walls, block walls and concrete surfaces. For application on smooth concrete surfaces, key coat or roughening of the receiving surface is required. E.MIX Easi Render 09 can also be used for patching and repairing concrete. It is intended to replace conventional cement-sand render. Ceramic tiles can be fixed on the E.MIX Easi Render 09 surface. E.MIX Easi Render 09 should not be used on painted surfaces or floors.

PRODUCT BENEFITS



FOR INTERIOR & EXTERIOR



SINGLE COMPONENT



EASY TO APPLY



BUILDING WALLS

TECHNICAL DATA & PHYSICAL PROPERTIES


Colour	: Grey
Binder	: Cement
Filler	: Graded silica sand
Aggregate Size	: 2.5 mm max
Additives	: Water soluble additives to improve workability, water retention, durability and adhesion
Density	: 1.8 kg/L (Dry) : 1.9 kg/L (Wet)
Pot Life	: Approx. 1 hours
Coat Thickness	: 5 - 15 mm per coat
Coverage	: Approx. 1.6 kg/ m ² /mm thick
Water demand	: Approx. 6.8 - 7.6 liters / 40 kg bag

USAGE

- Interior and exterior cement render for:
 - Brick walls
 - Block walls
 - Concrete surfaces
- Suitable for patching and repairing concrete

FEATURES AND BENEFITS

- Specific design for spray plastering
- Shrinkage compensated: reduce the chance of shrinkage cracks
- Suitable to receive paint with **E.MIX Skim Coat** series products
- Single component: fixed mixing proportion, ensure the quality of work
- Compatible to cementitious **Weber waterproofing** products
- Convenient: premixed to replace conventional cement sand render
- Suitable for tiling with receiving **Weber Tile Adhesive** and **Weber Tile Grout** series products



SAINT-GOBAIN WEBER (M) SDN BHD

No 29 & 31, Jalan TIAJ 2/1, Taman Industri Alam Jaya, 42300 Bandar Puncak Alam, Selangor D E, Malaysia



(603) 60389498/97/89



(603) 6038 9507



info.webermalaysia@saint-gobain.com



www.saint-gobain.my

E.MIX EASI RENDER 09

PREMIXED CEMENT RENDER FOR BRICK, BLOCK AND FAIRFACE CONCRETE WALL,
PATCHING AND GENERAL USE IN DRY OR WET INTERIOR AND EXTERIOR

PREPARATION

- Ensure the substrate is clean, structurally sound, adequately true and level to achieve specified tolerances, free from contamination, loose particles, grease, lacquer, plastics or traces of foreign materials, and protrusions such as wood peels, nails, excess mortar or any joints with tolerance that cannot be covered by the thickness of plaster.
- All cutting, chasing, fixing of concealed conduits, service outlets, fixing pads and the like and making good of the background are completed.
- All concrete surfaces should be properly cured prior to plastering.
- Substrate is to be moistened overnight and also at the time before the installation. No stagnant or frequent water flow on substrate is allowed immediately prior to installation.
- Smooth substrate like reinforced concrete wall (precast or cast in-situ), surface preparation like spatterdash (E.MIX Easi Render 09 + webermix multibond) or bonding agent (weberprim SP1) is required.

APPLICATION / USAGE

- Remove dust, loose particles, grease and traces of foreign materials. Dampen the dry absorbent surface before application of E.MIX Easi Render 09
- Mix one bag (40 kg) of E.MIX Easi Render 09 in approximately 6.8 – 7.6 liters of clean water using electrical hand mixer. A suitable mixing time is 3 – 7 minutes depending on the type of mixing equipment. For better mixing, it is advisable to use more than 700 rpm electrical mixer.
- The wear resistance and adhesion of the render can be improved by adding **webermix multibond**. In hot and dry conditions the plaster should be cured with water spray during the first 2 days
- Apply the E.MIX Easi Render 09 on the wall with desired thickness by steel trowel. When applying several layers, the layer underneath must be dried before application of the subsequent layer.
- Wall rendering of 5 – 15 mm thick should be in 1 coat. Wall rendering of 15 – 25 mm thick should be applied with 2 coats on the same day on spatterdashed concrete or blockwork. Second coat should be applied 5 – 6 hours after the first coat and first coat has to be at least 80 – 90% dried or touched hard and the surface need to scratch or left coarse before the application of the second coat.
- The mixture of E.MIX Easi Render 09 in the pot must be used within 2 hours.
- Natural air curing for E.MIX Easi Render 09 is enough. Water mist is not required for interior application. However, water mist is requested under the extreme hot or dry weather condition. Minimum 7 days curing is required for receiving paint or fixing tiles.

PROTECTION

- Recommend to wear HIOSH approved or equivalent particulate facemask when mixing the material.
- Material contains cement, which may produce an allergic effect.
- Material may cause irritation to eyes and skin. In case of contact with eyes, rinse immediately with plenty of water and seek medical assistance. After contact with skin, wash immediately with plenty of soap and water.
- Keep out of reach of children.

Note :

Because it is not possible to give specific instructions for the various site conditions or to control the applications, the information on this technical data sheet is for general guidance only

E.MIX EASI RENDER 09

PREMIXED CEMENT RENDER FOR BRICK, BLOCK AND FAIRFACE CONCRETE WALL,
PATCHING AND GENERAL USE IN DRY OR WET INTERIOR AND EXTERIOR

COVERAGE

Approximately 1.6 kg/ m²/mm thick
Approximately 1.6 m² / 15 mm thick / 40 kg bag

PACKING

Available in 40kg bag

SHELF LIFE / STORAGE

6 months if stored in a dry place.

TECHNICAL SERVICES

For further details or recommendation please contact our Technical Advisory / Specification Center at 603-6038 9498 (KL) & 604-626 2830 (Penang)

PRECAUTION

Avoid inhaling dust. If material enter eyes, wash out immediately with Clean Water. May cause minor skin irritation; therefore use suitable gloves. Keep out of children reach.



SAINT-GOBAIN WEBER (M) SDN BHD

No 29 & 31, Jalan TIAJ 2/1, Taman Industri Alam Jaya, 42300 Bandar Puncak Alam, Selangor D E, Malaysia



(603) 60389498/97/89



(603) 6038 9507



info.webermalaysia@saint-gobain.com



www.saint-gobain.my